

POLYBUTENE COMPARISON CHART

Molecular Weight	K.V. cSt 38oC	K.V. cSt 40oC	K.V. cSt 50oC	K.V. cSt 98.9oC	K.V. cSt 100oC	Soltex PB	Ineos Indopol	TPC ePB Grades Product #	TPC HR-PIB Product #
320		24 - 30						ePIB	HR-PIB
360		21 - 45		7 - 9		PB 6	L-14	135	535
407					55 - 70	PB 7			
420		94 - 100					L-50		
440				12 - 14	11 - 14				
460	210 - 227	100 - 130				PB 8	H-8	145	545
510		210 - 230				PB 10			
540					23 - 37	PB 12			
560					27.5 - 33.5		H-15		
610					48.5 - 55.5		H-25		
650				65 - 87	51 - 64				
660					70 - 78		H-35		
670					41 - 59	PB 16			
700					70 - 90	PB 18		175	575
750					100 - 115		H-50		
780				97 - 120	92 - 114				
856					110 - 120	PB 20			
920					200 - 235		H - 100		
950					190 - 240	PB 24		1105	5105
1000				214 - 257	205 - 245				
1290					605 - 655		H - 300		
1300				622 - 686	580 - 680	PB 32		1160	5160
2060					2900 - 3200		H-1500		
2100				3000 - 3400	2850 - 3280				
2225					2200 - 2950	PB 122		1285	5285
2300					3900 - 4200		H-1900		
2400				4100 - 4800	3900 - 4600				
3000					4000 - 4800	PB 128		1350	5350
3800				12000 - 14000	11100 - 13300				
5800				39000 - 47000	36000 - 45000		H-6000		
			10 - 12						