



*Adding value to
your formulations*

FALEX TEST RESULTS¹

(Run to Failure)

<u>PRODUCT</u>	<u>LOAD CAPABILITY (LBS)</u>
RF 150 with 1.25% S8478*	1300
RF 300	560
RF 300 with 1.25% S8478*	1350
2.00% S8478*	1310
1.25% S8478* (R-12 Bubble)	1330
2% S8478*	1330
.1% Lubrizol 1097	880
.5% S8478*	1075
Mobil DTE	1240

*Synoad 8478

¹All with R-22 bubbled through unless otherwise indicated.