



*Adding value to
your formulations*

SEALED TUBE STABILITY, % R-22

SYNTHETIC ALKYLATE FLUIDS

	<u>%R-22, 14 DAYS</u>
RF 150	0.02
RF 300	0.03
Mineral Oil	0.6