



Adding value to
your formulations

RF 150

**SHELL FOUR-BALL WEAR TEST
(ASTM D-2266)¹**

<u>OIL</u>	<u>SCAR DIAMETER, mm</u>
RF 150	0.50
RF 150, 0.5% S8478*	0.22
RF 300	0.45
RF 300, 0.5% S9478*	0.25
Mineral Oil	0.50

¹1800 RPM, 5 kg, 75 C (158 F), 1 hour

*Synoad 8478