

## ThixoCal™ 5060

### *Lower Viscosity Partially Formulated Corrosion Preventive Compound*

ThixoCal™ 5060 is a partially formulated corrosion preventive compound comprised of a gelled calcium sulfonate and a variety of other film forming ingredients. ThixoCal™5060 may be used as is or further formulated with waxes, resins, and other ingredients to form coatings that exhibit excellent salt spray protection. The moderately low viscosity of ThixoCal™5060 makes handling convenient and provides for easy incorporation of other blending components.

#### **TYPICAL PROPERTIES** (*not specifications*):

<u>PROPERT</u>	<u>AST</u>	<u>TYPICA</u>
% NON VOLATILE BY WEIGHT	Soltex 001	60 - 63
VISCOSITY, CPS, RV5@10	D2196	14,000 – 19,000
FLASH POINT, °C	D7094/D93	38 min.
DENSITY @ 25°C, pounds/gallon	D1475	7.5 - 7.84

#### AVAILABILITY

ThixoCal™ 5060 is available in drums or bulk.

#### SAFETY, HANDLING AND STORAGE

ThixoCal™ 5060 contains mineral spirits and should be stored away from heat, flame and sources of ignition. Prolonged breathing of vapors should be avoided. Consult MSDS for further precautions and handling advice.

No warranties, express or implied, including warranties of merchantability or fitness for a particular use are made with respect to the products described herein. Nothing contained herein shall constitute permission or a recommendation or inducement to practice any invention covered by a patent without the permission of the patent owner. Customers/users are advised to test the product in advance to make certain it is suitable for their particular production conditions and use or uses of the product. Seller shall not be liable for and the customer assumes all risk and liability for any use or handling of the product.

Date: 07/06/2010